



INSTANT ADHESIVE ACTIVATOR AEROSOL

TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M745-2012	INSTANT ADHESIVE ACTIVATOR AEROSOL

PRODUCT DESCRIPTION:

Mohawk's Aerosol Activator is used to speed the cure of the Instant Adhesive product line. Cyanoacrylate glue activator in aerosol form, makes using CA's easier and safer than ever. The can will not spill or leak like pump type activators, and the fine atomization and consistent coverage promote more even curing. The carrier solvent reduces "chlorosis", the whitening often experienced with other activators. Technicians have reported using less activator than with the pump types, with less mess. 10 oz.

ADVANTAGES:

1. Easy to use.
2. Cure time is drastically reduced.
3. Non-yellowing.
4. Finer – more controllable mist than with pump type activator.
5. More economical – you use less product than with pump type activator.

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	accelerator for cyanoacrylate adhesives
Color	none
Sheen	none
Viscosity	N/A
WPG	5.322265047 lbs/gal
Solids by Volume	0.000000000 ±1%
Solids by Weight	0.000000000 ±1%
Flash Point	-68.800000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	637.745731527 g/l
Coating VOC (Lb/Gal)	5.322265047 lbs/gal
Material VOC (g/l)	637.745731522 g/l
Material VOC (Lb/Gal)	5.322265047 lbs/gal
#VOC/#Solid	0.000000000 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000000000
Spread Rate	0.000000000 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A

DIRECTIONS:

Activator significantly speeds curing. Spray sparingly about 11 inches from target contact surface, apply adhesive to the opposite surface, and assemble. Or apply adhesive, assemble parts, and spray activator topically over joint area. Do not wipe spray that comes in contact with finished surface while wet.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.