



# LEATHER REVIVE 8 OZ.

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M850-10074	LEATHER REVIVE 8 OZ.

### PRODUCT DESCRIPTION:

Pull-Up Revive contains the same type of formulation applied at the tannery by machine. Pull-Up Revive transfers this process to a hand application to enable the renewing of pull effect leathers outside of the tannery. Over time, the tannery applied pull effect will diminish with use. This is most evident by a lightening of the leather in high use areas. PullUp Revive will renew and restore pull-up effect leathers. It will also improve scratches caused by fingernail marks, scuffing, etc.

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Water based
Color	Creamy - Dries Clear
Sheen	N/A
Viscosity	Brookfield Viscosity 3600 cps
WPG	8.389936662 lbs/gal
Solids by Volume	7.865710454 ±1%
Solids by Weight	8.354755870 ±1%
Flash Point	200.000000000 °F
HMIS	H: 1, F: 0, R: 0, P: X
Coating VOC (g/l)	1.757929296 g/l
Coating VOC (Lb/Gal)	0.014670683 lbs/gal
Material VOC (g/l)	0.138503998 g/l
Material VOC (Lb/Gal)	0.001155876 lbs/gal
#VOC/#Solid	0.001648993 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000653919
Spread Rate	126.165995682 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	12 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	As needed
PH	7

Water - CAS 7732-18-5 - solvent  
PEG-60 Lanolin - CAS 61790-81-6 - hydrophobe, softener, lubricant  
Proprietary Wax - CAS not available - hydrophobe  
Triethanolamine - CAS 102-71-6 - surfactant, emulsifier  
Proprietary Rheology Modifier - CAS not available - rheology  
Methylparaben - CAS 99-76-3 - preservative  
Fats and Glyceridic oils, sesame - CAS 8008-74-0 - hydrophobe

Beeswax - CAS 8012-89-3 - hydrophobe  
Formaldehyde - CAS 50-00-0 - not intentionally added  
Ethylene Oxide - CAS 75-21-8 - not intentionally added

---

#### DIRECTIONS:

Leather Type Usage: Pull-Up leathers Shake well. Pre-test onto a hidden area. After drying check outcome. If not satisfied with results, do not use. Apply to a sponge or lint-free cloth and rub lightly into surface scratches or areas needing restoration. A hair dryer will assist the product activation. Heat deep scratches as you massage the area. A second application may be needed. Routine Care: Use Pull-Up Revive as needed to keep your pull-up effect leathers looking new

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.