

Ficha Técnica

Pin Sport Water-Based Emulsion Paint. For Sports Courts



Acrylic Paint

Versión: 28/09/2022



Descripción

One-component coating based on water-based acrylic resins, with great hardness and adherence. Very resistant to abrasion and weathering due to its colors, solid to light. Anti dust.

Propiedades

- Great hardness and adhesion.
- Highly resistant to abrasion and weather.

Certificados de producto

UNE 41901:2017EX, determination of resistance to sliding by the friction pendulum for pedestrian traffic. Wet test. Category 3 (maximum).

Test number: 20/22092-508 S and 20/22092-509 S.

Certificate issued by an approved external laboratory available to the client who requests it.



Certificados de empresa



Datos técnicos

Datos de identificación del producto

Color	Negro (Black) , Blanco (White) Gris Oscuro RAL 7001 (Dark Grey RAL 7001), Gris Claro RAL 7035 (Light Grey RAL 7035), Rojo Óxido (Oxide Red), Vercé Cromo (Chrome Green), Verde Oscuro (Dark Green) y Azul (Blue)
Aspecto	Matt
Naturaleza	Acrylic Copolymers

Datos de aplicación del producto

Herramienta	Brush, roller, spray or airless
Rendimiento	9 - 12 m ² /L/Coat
Diluyente	Thinner for water-based paints and enamels
Repintado	6 hours
Secado	30 - 45 minutes

Dónde aplicarlo

Due to its great hardness, resistance to the exterior and abrasion, it is ideal for painting cement and concrete surfaces dedicated to sports activities: tennis, racquetball, etc. Decorative and anti-dust protector on concrete and mortar. Good behavior in areas such as sidewalks, islands, etc.

Particularly suitable for cement floors and pavements, mortars and asphalts in good condition, subjected to the passage of people and medium vehicles such as bicycles and mopeds.

Precauciones



- Do not apply at temperatures below 5°C or above 30°C.
- Do not apply with risk of frost or rain.
- Do not apply in conditions of strong winds or in direct sunlight.
- Avoid using different batches in the same cloth or, failing that, mix the current can with the next one at 50% to reduce the normal differences between batches.

Productos relacionados

SELLACRYL

Modo de empleo

ON NEW, CLEAN, DRY SURFACES FREE OF RUST, GREASE OR SALTPETER OF:

- Cement and concrete: Once set. Directly, diluting up to 10% for the first coat.

ON OLD PAINTED SURFACES:

- With paints in good quality condition: Wash and sand lightly, putty if necessary and apply afterwards.
- With paintings in poor condition: Remove and proceed as a new surface. If alkalinity is detected on the support, it must be corrected.
- Anti-slip version: To obtain a product with the highest anti-slip category, add 100 g of silica sand (55/60) or reflective glass microspheres (EchoStar 5) to each liter of product. Shake until perfect homogenization.

The pavements must be completely set, clean of efflorescence, neutralized if they have an alkaline character. Also, if necessary, the pore should be opened to improve adherence.

Almacenamiento

- In its original closed container, at non-extreme temperature and humidity.
- Keep away from direct sunlight.
- Maximum recommended since manufacture: 2 years.

Formatos

Containers of: 4 L & 15L



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com



Compromiso Medioambiental y Social Jafep

ARGENTINA

DUBAI

ESPAÑA

MARRUECOS

POLONIA

UCRANIA



www.jafep.com
jafep@jafep.com