



Slip Resistant Treatment For Mineral Surfaces

PRODUCT DESCRIPTION

PureKleen-AS

- ⇒ Ensures that using a simple process, slippery surfaces become low-slip.
- ⇒ Can be applied to mineral surfaces, ceramic, concrete and terrazzo tiles.
- ⇒ Does not materially alter the chemical composition of a surface.
- ⇒ Is for use in factories, communal areas, nursing homes, entrance halls, gyms, swimming pool surrounds, pedestrian crossings, kitchen floors, shower units ... and anywhere floors are slippery, especially when wet.
- ⇒ Materials prone to slip and contain significant amounts of silica, can have these effectively pitted giving an anti-slip effect that with minimal change to the aesthetics of a surface.
- ⇒ Is a product which is non-hazardous and can be easy to use.
- ⇒ Has a pleasant odour enabling it to be used anywhere, even in a closed room.

TECHNICAL DATA

- ⇒ Physical State at 20 °C : Liquid
- ⇒ Appearance : Colourless
- ⇒ Odour : Scented
- ⇒ pH : 4 ± 0.5
- ⇒ Boiling point [°C] : 100 °C
- ⇒ Density : 1.1
- ⇒ Solubility in water [vol/vol] : Fully soluble
- ⇒ Flash Point [°C] : Not applicable

PACKAGING

5L, containers

CHEMICAL PROPERTIES

Water-based alkali

EQUIPMENT CLEANING

Clean equipment with clean warm water.

STORAGE & SHELF LIFE

Store away from frost and heat in a dry place: temperature between 5 °C and 30 °C. Shelf life is 24 months from the production batch date when kept in the original unopened container.



Porcelain floor treated with PureKleen-AS

APPLICATION INSTRUCTIONS

"Always test apply on a small hidden portion of the substrate"

Guide treatment times:

- For **concrete, terrazo slabs**: Use neat (allow to react for upto 60 minutes).
- For **slabs, porcelain, tiles**: Use neat (allow to react for upto 40-60 minutes).
- For **polished granite**: Use neat (allow to react for upto 40-60 minutes).

Apply the product onto clean and dry surface applying it with the assistance of a brush or a low-pressure spray. Make sure the product stays present over the complete surface during treatment. Top-up with more product as required.

Do not allow a treated surface to become dry throughout the treatment period

After treatment, rinse carefully with water. The treated surface can be used immediately it becomes dry. Repeat the operation again if additional slip-resistance is required, depending on the floor and the resistance level measurement.

HEALTH & SAFETY

See Material Safety Data Sheet before use.

KEEP OUT OF THE REACH OF CHILDREN

Important: The content of this documentation is based on our experience of the product. Rocan Products Ltd guarantees the quality of its products, but expressly declines any liability in the event of failure by the user to comply with the recommendations and conditions of use of said products, notably but not exclusively in the event of incorrect application, application by unqualified personnel, use of products not compatible with Rocan's products or bad weather conditions. For further information, refer to the safety data sheet.

ROCAN PRODUCT CODE: R-16/A

Date of last update: 19.09.15