
TECHNICAL DATA SHEET

VUNEX

SPECIAL ADHESIVE FOR CONCRETE, IN SOLUTION OF POLYCHLOROPRENE, SYNTHETIC RESINS AND PROMOTERS OF ADHESION IN SOLVENT MIXTURE OF ALIFATIC HYDROCARBONS, AROMATICS, TOLUENE AND KETONES. CAN BE USED AS A BICOMPONENT, COMBINED WITH ISOCIANATES

GENERAL USE CONTACT ADHESIVE INDICATED FOR WOOD, CORK, FABRICS, LEATHER, RUBBER, ETC ...

ASPECT: LIGHT YELLOW LIQUID

OPEN TIME: 24 h.

BROOKFIELD VISCOSITY: 2400-3200 mPa. S at 20 ° C.

DRY RESIDUE: 24% (+/- 1.5).

DENSITY: 0.85 g / cc. at 20 ° C.

FLAMMABILITY: FLAMMABLE LIQUID WITH POINT OF INFLAMMATION LOWER AT 21°C.

OPEN TIME: 2-4 h, DEPENDING ON SUBSTRATES AND ENVIRONMENTAL CONDITIONS

STORAGE: IN THE ORIGINAL PACKAGING BETWEEN 10 and 25 °C (low temperatures will increase the viscosity, the effect being reversible)

THE ADHESIVE HAS A LIFE OF 12 MONTHS.

HOW TO USE: APPLY IN FINE COAT (A THICK COAT DOES NOT IMPLY BETTER ADHESION), BY BRUSH OR ROLLER, ON THE TWO FACES TO JOIN. KEEP THEM SEPARATE FOR APPROXIMATELY 10 MINUTES TO ALLOW THE EVAPORATION OF THE SOLVENT. AFTER SUCH TIME SPACE, PRESS BOTH PARTS, IN ALL ITS SURFACE, FOR 5-10 SECONDS. THE PARTS CAN BE HANDLED IMMEDIATELY.

DUE TO THE DIVERSITY OF MATERIALS AND TO THE DIFFERENT WORKING CONDITIONS THAT MAY BE GIVEN, WE DO NOT ASSUME RESPONSIBILITY REGARDING THE USE OF THIS INFORMATION EXCEPT IN THE CASES IN WHICH THE USE OF OUR PRODUCTS IS UNDER OUR CONTROL.

OUR CUSTOMERS MUST BE SURE OF THE SUITABILITY OF OUR PRODUCTS TO THE PROCESSES AND MATERIALS TO BE USED.